SUNTUF® Beehive

Embossed Corrugated Polycarbonate Sheet



Special technology for better hail resistance with unique solar colours only from Palram



Main Benefits

- UV Protection prevent 99.9% of UV radiation
- Greater Hail resistance
- 100% diffused light and reduced glare
- High wind resistance



SUNTUF® Beehive



Typical Applications

Pergolas and gazebos

Patio enclosures

Covered walkways

Canopies and overhangs

Sunrooms

Carports





Product Availability

Colours	Clear, Grey, Solar Ice
Textures	Prismatic-honeycomb
Thickness	2.8 mm
Width	860 mm

Profile	Drawing	
76/18 Iron	~~~~	

Solar Properties

	LT (%)	SC	SHGC
Clear	90	1.01	0.88
Grey	20	0.34	0.29
Solar Ice	25	0.44	0.38

Please note: Minimum required roof pitch is 5 degrees.

Span Data

Corrugated Profile

Max Mid Span	1400mm
Max End Span	1100mm

Flammability

SUNTUF® Beehive complies with the most demanding international fire resistance standards in the field of plastics, as indicated in the detailed table herein. The classification is subject to product type, thickness and color.

Australian Standard: AS/NZS 1530.3:1999 European Standard: EN 13501 - B s1, d0

*For more detailed information please contact your Palram distributor.



PALRAM SA/NT 517A Cross Keys Road Cavan SA 5094 Tel: (08) 8262 2288 Fax: (08) 8262 3388

salessa@palram.com

PALRAM NSW/ACT

Unit 2, 26 Redfern St. Wetherill Park, NSW 2164 Tel: (02)8788 6100 Fax: (02) 8788 6199 salesnsw@palram.com

PALRAM QLD

Unit 9C / 380 Bilsen Road Geebung QLD 4034 Tel: (07) 3172 5581 Fax: (07) 3172 5516 salesqld@palram.com

PALRAM VIC/TAS

34 Buys Court Derrimut VIC 3030 Tel: (03) 9219 4444 Fax: (03) 9219 4455 salesvic@palram.com PALRAM WA

74 Christable Way Landsdale WA 6065 Tel: (08) 9302 4173 Fax: (08) 9302 5287 saleswa@palram.com



as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the ment of any patent. Palram industries or its distributors cannot be held responsible for any losses incurred through incorrect ion of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.



